

SAKRETE®

CONCRETE MIX

DESCRIPTION

A ready to use concrete mixture of fine and coarse aggregate and portland cement. Ingredients are mixed to meet specified strength requirements.

USES

To be used where a 5.08 cm (2") thickness or more is needed. For making walks, floors, footings, patios, steps, setting posts and poles.

DIRECTIONS

Empty contents of sack into mortar box, wheel barrow or onto a smooth surface. Form a crater for adding water. Add clean water at the rate of 2.7 litres (2¹/₃ quarts) per 30 kg bag and mix thoroughly. If too stiff, add more water, a cupful at a time. Avoid a soupy mix. In cold weather use warm water to accelerate the set. Protect from freezing until cured. (For repairing, remove all foreign material and dampen adjoining old concrete.) After pouring SAKRETE Concrete Mix, tamp mix with rod or stick. Level the work with a straight edged board. After leveling, allow concrete to set about one (1) hour before troweling. For a rough surface use a wood float, then for textured roughness use broom or brush. For a smooth surface use a steel trowel. Use edging tool. Allow to set one (1) day, then keep moist for at least three (3) days by an occasional fine spraying of water.

PACKAGING

Packaged in 30 kg (66 lb) multi-ply, moisture proof bags.

COVERAGE

30 kg (66 lb) bag approximately 0.6 m² at 2.54 cm thickness (6½ sq. ft. at 1 inch).

Wet Volume: 0.014 m³ (½ ft.³).

SPECIFICATIONS

Will meet or exceed 3,500 PSI (24 MPA). Exceeds strength requirements of ASTM Spec. C-387 when used as directed.

IMPORTANT

Store in a dry place.

CAUTION

Avoid contact with eyes. Avoid ingestion or inhalation. Contains cement which, when mixed with water, forms a calcium hydroxide solution. Avoid contact with skin, including contact with saturated clothing.

FIRST AID TREATMENT: If splashed in eyes or on skin, flush thoroughly with water.